

ENAMEL PLUS HRi FLOW^{HF}

Material to be used in posteriors as cavity liner for direct and indirect restorations (before taking the impression) and in anteriors for class V.

- Highly Filled
- Higher Viscosity & Elasticity
- Higher Radiopacity & High Physical Properties
- No bubbles



PHYSICAL CHARACTERISTICS

	FILLER (Weight) %	VICKERS HARDNESS MPa	YOUNG MODULUS MPa	FLEXURAL STRENGTH MPa	COMPRESSIVE STRENGTH MPa	RADIOPACITY
Flow HF	77	770	13485	148	394	210% Al
Standard Flow	55	350	6000	120	350	30% Al

Ref	Description	Q.ty
CHR1F	ENAMEL PLUS HRi FLOW Intro Kit Dentine syringe: UD1 (A1), UD2 (A2), UD3 (A3), UD3,5 (A3,5), UD4 (A4), UD5, UD6. Black tips ø 1,2 mm Plexiglass holder	7x2 g 25 pcs 1 pc
CHRFUDO	HRi Flow UDO refill + 3 tips	2 g
CHRFUDO,5	HRi Flow UDO,5 refill + 3 tips	2 g
CHRFUD1	HRi Flow UD1 (A1) refill + 3 tips	2 g

Ref	Description	Q.ty
CHRFUD2	HRi Flow UD2 (A2) refill + 3 tips	2 g
CHRFUD3	HRi Flow UD3 (A3) refill + 3 tips	2 g
CHRFUD3,5	HRi Flow UD3,5 (A3,5) refill + 3 tips	2 g
CHRFUD4	HRi Flow UD4 (A4) refill + 3 tips	2 g
CHRFUD5	HRi Flow UD5 refill + 3 tips	2 g
CHRFUD6	HRi Flow UD6 refill + 3 tips	2 g
CHRF25	Tips 1,2 mm	25 pcs
PLEX11	Plexiglass holder x 11 Flow syringe holes	1 pc

Low viscosity flowable composite



ENAMEL PLUS HFO FLOW

Ref	Description	Q.ty
CHF1F	ENAMEL PLUS HFO FLOW Intro Kit Dentine syringe: UD1 (A1), UD2 (A2), UD3 (A3), UD3,5 (A3,5), UD4 (A4), UD5, UD6. Black tips ø 1,2 mm Plexiglass holder	7x2 g 25 pcs 1 pc
CHFFUD1	HFO Flow UD1 (A1) refill + 3 tips	2 g
CHFFUD2	HFO Flow UD2 (A2) refill + 3 tips	2 g
CHFFUD3	HFO Flow UD3 (A3) refill + 3 tips	2 g
CHFFUD3,5	HFO Flow UD3,5 (A3,5) refill + 3 tips	2 g
CHFFUD4	HFO Flow UD4 (A4) refill + 3 tips	2 g
CHFFUD5	HFO Flow UD5 refill + 3 tips	2 g
CHFFUD6	HFO Flow UD6 refill + 3 tips	2 g
COSHF3	HFO Flow B3 refill + 3 tips	2 g
COSHF4	HFO Flow B4 refill + 3 tips	2 g
CHFF25	Black tips ø 0,8 mm	25 pcs

Highly flowable body with high elasticity and calibrated light diffusion that reproduces protein layer of natural tooth

- Increases the internal light diffusion in direct and indirect restorations, reducing the decrease in value typical of the vitreous masses (no need with HRi Universal Enamel).
- Increases the dentine fluorescence of non vital teeth.

GLASS CONNECTOR



Ref	Description	Q.ty
COSHFOGFC	Enamel plus HFO Glass Connector + 3 tips	1 g